



Notation of a product: AKC-30

The specification of a product	O'z Dst 1056:2014	Values reached during enrichment
1.Elemental composition, % a) Mass lobe of alumina(Al_2O_3), % not less b) Mass lobe of iron oxide (Fe_2O_3), % no more v) Mass lobe of silicon dioxide (SiO_2), % no more r) Mass lobe of titanium oxide (TiO_2), % no more	30 ± 2 0,8 55,0 0,5	28-32 0,5-0,8 52,0-55,0 0,45
2. Mass lobe of a moisture, %	no more 20,0	15-20
3. Hydrogen ionization value not less	7,5-9,5	7,5-8,4
4. Bending strength in a dry condition, H/MM2 not less, %	0,8	0,8 – 1,0
5. Fire losses, % no more	12,5	11,9-12,3
6. Rest (remainder) of wet screening (screen 0045), more than 45 microns, in % not less	0,5	0,3 - 0,5